


کد مدرک : FO-28-03/01	<b>Nia Shimi Manufacturing &amp; Trading Co.</b> Corrosion Protection of water, Oil & Gas Pipelines <b>DATA SHEET</b>	شرکت تولیدی بازرگانی نیا شیمی (سهامی خاص)	
سند مرجع : PR-28			
صفحه: از			

**Product Name:**

Mastic Filler

**Trade Name:**

NST-MF

**Manufacture Date:**

**Batch No. :**

Random samples have been taken from above batch. Test results are as following:

	Unit	Result	Specification	Test Method
Color	-	Black	Black	ASTM D1000
Total thickness, min	mm	3	3±10%	ASTM D1000
Peel strength at 23 °C , min	N/mm	4.8	3	EN 12068 Annex C
Lap shear strength at 23 °C , min	N/mm <sup>2</sup>	0.38	0.25	EN 12068 Annex D
Softening point , min	°C	103	100	ASTM E 28

No. 16, Toupchi st., Northern Sohrevardi St., Tehran, Iran

Postal Code: 1558841010

Tel: +9821 88737228

Fax: +9821 88736384

E-mail: [niashimi@accir.com](mailto:niashimi@accir.com)

تاریخ بازنگری فرم: ۱۳۹۶,۰۷,۰۱	تاریخ ایجاد فرم: ۱۳۹۴,۰۳,۱۲
-------------------------------	-----------------------------